

FINAL REPORT

Report ID : 204774

Report Information

Submitting Organisation : 00121970 : Tef-Gel Pty Ltd
Account : 143012 : Tef-Gel Pty Ltd
AWQC Reference : 143012-2017-CSR-1 : Prod Test: Tel-Gel
Project Reference : PT-3092
Product Designation : Tef-Gel Lubricant
Composition of Product : PTFE.
Product Manufacturer : Tef-Gel Pty Ltd., Queensland, AUSTRALIA.
Use of Product : In-Line/Anti-Corrosive and Anti-Seize Lubricant.
Sample Selection : As provided by the submitting organisation.
Testing Requested : **AS/NZS 4020:2005 TESTING OF PRODUCTS FOR USE IN CONTACT WITH DRINKING WATER**
Product Type : Composite
Samples : Samples were prepared and controlled as described in Appendix A of AS/NZS 4020:2005
Extracts : Extracts were prepared as described in Appendix C, D, E, F, G, H.
Project Completion Date : 18-May-2017
Project Comment : The results presented herein demonstrate compliance of Tef-Gel Lubricant to AS/NZS 4020:2005 when exposed at area to volume ratios up to 1000 mm²/L at 100°C ± 2°C.

PLEASE NOTE THAT THIS REPORT SHALL NOT BE REPRODUCED EXCEPT IN FULL

THE RESULTS STATED IN THIS REPORT RELATE TO THE SAMPLE OF THE PRODUCT SUBMITTED FOR TESTING. ANY CHANGES IN THE MATERIAL FORMULATION, PROCESS OF MANUFACTURE, THE METHOD OF APPLICATION, OR THE SURFACE AREA-TO-VOLUME RATIO IN THE END USE, COULD AFFECT THE SUITABILITY OF THE PRODUCT FOR USE IN CONTACT WITH DRINKING WATER



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

Summary of Results

APPENDIX	RESULTS
C – Taste of Water Extract	Passed at an exposure of 1000 mm ² per Litre.
D – Appearance of Water Extract	Passed at an exposure of 1000 mm ² per Litre.
E – Growth of Aquatic Micro-organisms	Passed at an exposure of 1000 mm ² per Litre.
F – Cytotoxic Activity of Water Extract	Passed at an exposure of 1000 mm ² per Litre.
G – Mutagenic Activity of Water Extract	Passed at an exposure of 1000 mm ² per Litre.
H – Extraction of Metals	Passed at an exposure of 1000 mm ² per Litre.

Test Methods

Test(s) in Appendix	AWQC Test Method	Reference Method
C	T0320-01	AS/NZS 4020:2005
D	TO029-01 & TO018-01	APHA 2130b
E	TO014-03	APHA 4500 O C
F	TM-001	AS/NZS 4020:2005
G	TM-002	AS/NZS 4020:2005
H	TIC-006	EPA 200.8

Summary Comment : Product range to include 10g, 30g, 60g, 120g, 320g, 500g and 1kg quantities.

FINAL REPORT

Report ID : 204774

CLAUSE 6.2 Taste of Water Extract

Sample Description	The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm ² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
Extraction Temperatur	100°C ± 2°C.
Test Method	Taste of Water Extract (Appendix C)
Test Information	
Scaling Factor	Not applied.
Results	Not detected.
Evaluation	The product passed the requirements of clause 6.2 when tested at an exposure of 1000 mm ² per Litre.
Number of Samples	2.
Test Comment	Not applicable.



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

CLAUSE 6.3 Appearance of Water Extract

Sample Description The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperatur 100°C ± 2°C.

Test Method Appearance of Water Extract (Appendix D)

Scaling Factor Not applied.


Results

	<u>Test (- Blank)</u>	<u>Maximum Allowed</u>	<u>Units</u>
Colour	<1	5	HU
Turbidity	0.2	0.5	NTU

Evaluation The product passed the requirements of clause 6.3 when tested at an exposure of 1000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Andrew Ford
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

CLAUSE 6.4 Growth of Aquatic Micro-organisms

Sample Description The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm² per Litre. Extracts were prepared using 1000 mL volumes of test water.

Test Method Growth of Aquatic Micro-organisms (Appendix E)

Inoculum The volume of the inoculum was 100 mL

Scaling Factor Not applied.

Results

Mean Dissolved Oxygen	Control	7.6 mg/L
Mean Dissolved Oxygen Differenc	Positive Reference	5.0 mg/L
	Negative Reference	0.1 mg/L
	Test	0.10 mg/L

Evaluation The product passed the requirements of clause 6.4 when tested at an exposure of 1000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Thuy Diep
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

CLAUSE 6.5 Cytotoxic Activity of Water Extract

Sample Description	The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm ² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.
Extraction Temperatur	100°C ± 2°C.
Test Method	Cytotoxic Activity of Water Extract (Appendix F)
Scaling Factor	Not applied.
Results	Non-cytotoxic.
Evaluation	The product passed the requirements of clause 6.5 when tested at an exposure of 1000 mm ² per Litre.
Number of Samples	1.
Test Comment	The test extracts and blank extracts were used to prepare nutrient growth medium and subsequently used to grow a cell line (ATCC Number CCL 81) in the analysis. In addition zinc sulphate (0.4 mmol) was used for the positive control in the analysis.



Brendon King
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

CLAUSE 6.6 Mutagenic Activity of Water Extract

Sample Description The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperatur 100°C ± 2°C.

Test Method Mutagenic Activity of Water Extract (Appendix G)

Scaling Factor Not applied.

Results

Bacteria Strain	Number of Revertants per Plate				
	S9	Blank	Sample Extract	Positive Controls	
<i>Salmonella typhimurium</i> TA98	-	40, 41, 40	42, 34, 44	2884, 2905, 2895	<u>NPD</u> (20µg)
Mean ± Standard deviation		40.3 ± 0.6	40.0 ± 5.3	2894.7 ± 10.5	
	+	54, 35, 56	30, 39, 29	2551, 2276, 2962	<u>2-AF</u> (20µg)
Mean ± Standard deviation		48.3 ± 11.6	32.7 ± 5.5	2596.3 ± 345.2	
<i>Salmonella typhimurium</i> TA100	-	631, 663, 620	619, 541, 598	1277, 1286, 1316	<u>Azide</u> (1.0µg)
Mean ± Standard deviation		638.0 ± 22.3	586.0 ± 40.4	1293.0 ± 20.4	
	+	333, 356, 337	330, 349, 348	1623, 1575, 1585	<u>2-AF</u> (20µg)
Mean ± Standard deviation		342.0 ± 12.3	342.3 ± 10.7	1594.3 ± 25.3	
<i>Salmonella typhimurium</i> TA102	-	654, 592, 697	617, 690, 631	2562, 2630, 2669	<u>Mitomycin C</u> (10µg)
Mean ± Standard deviation		647.7 ± 52.8	646.0 ± 38.7	2620.3 ± 54.2	
	+	619, 773, 838	766, 650, 695	2446, 2422, 2533	
Mean ± Standard deviation		743.3 ± 112.5	703.7 ± 58.5	2467.0 ± 58.4	

Comments S9 was used as a metabolic activator. NPD (4-nitro-o-phenylenediamine), Azide, and Mitomycin C are specific positive controls for strains TA98, TA100 and TA102 respectively while 2 - AF (2-aminofluorene) when used in conjunction with S9 is a positive control for both TA98 and TA100

Evaluation The product passed the requirements of clause 6.6 when tested at an exposure of 1000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Michael Glasson
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025

FINAL REPORT

Report ID : 204774

CLAUSE 6.7 Extraction of Metals

Sample Description The sample was applied on to a glass slide with dimensions 20 mm x 50 mm providing a surface area of approximately 1000 mm² per Litre. Extracts were prepared using 1000 mL volumes of 50 mg/L hardness water.

Extraction Temperatur 100°C ± 2°C.

Test Method Extraction of Metals (Appendix H)

Scaling Factor Not applied.

Method of Analysis All methods used to determine concentrations of metals are based on those described in the 21st edition of Standard Methods for the Examination of Water and Wastewater published by the APHA, AWWA and WEF (2005). The methods have been adapted for the instrumentation in use at the Australian Water Quality Centre. Concentration of the metals described in Table 2 of the AS/NZS 4020:2005 are determined as follows:

Antimony, Arsenic, Barium, Cadmium, Chromium, Copper, Lead, Mercury, Molybdenum, Nickel, Selenium and Silver by Inductively Coupled Plasma Mass

Results	Limit of Reporting mg/L	Blank mg/L	Test 1 mg/L	Test 2 mg/L	Max Allowed mg/L
Final Extract					
Antimony	0.0005	<0.0005	<0.0005	<0.0005	0.003
Arsenic	0.0003	<0.0003	<0.0003	<0.0003	0.007
Barium	0.0005	0.0239	0.0218	0.0214	0.7
Cadmium	0.0001	0.0002	<0.0001	<0.0001	0.002
Chromium	0.0001	0.0001	<0.0001	<0.0001	0.05
Copper	0.0001	0.0850	<0.0001	<0.0001	2.0
Lead	0.0001	0.0009	0.0002	<0.0001	0.01
Mercury	0.00003	<0.00003	<0.00003	<0.00003	0.001
Molybdenum	0.0001	<0.0001	<0.0001	<0.0001	0.05
Nickel	0.0001	0.0043	<0.0001	<0.0001	0.02
Selenium	0.0001	<0.0001	<0.0001	<0.0001	0.01
Silver	0.00003	<0.00003	<0.00003	<0.00003	0.1

Evaluation The product passed the requirements of clause 6.7 when tested at an exposure of 1000 mm² per Litre.

Number of Samples 1.

Test Comment Not applicable.



Dzung Bui
APPROVED SIGNATORY



Corporate Accreditation No.1115
Chemical and Biological Testing
Accredited for compliance with ISO/IEC 17025